



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315  
 P.O. Box 529, Mordialloc, Victoria, 3195  
 102-104 Malcolm Road, Braeside, Victoria, 3195  
 Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3806)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPDM)	Rubber (Natural)	Epoxy		
Acetaldehyde5	A	A	A		B	A	A	D			C		D	D	A		A	A	D	C	B	A	A	A	D	B	B	D	B	C	A		
Acetamide		B	A								C						B							A	A	A			A	A	D	A	
Acetate Solvent2	A	B	A	B	B			A	C	B	A		B	D	A		A		B	D			A	A	D	D	D	D	C	B	C	A	
Acetic Acid, Glacia1		B	A	A	B	A	A	C	C	D	A		C	B	A	C	D	D	D	B	B	A	A	A	D	D	B	C	D	B	C	B	
Acetic Acid 20%		B	A			A	A	C				A	B		A	A	D				A	A		A	A	C		C			B		
Acetic Acid 80%		B	A			A	A	C				A	D		A	B	D				B			A	A	C		D			B		
Acetic Acid		B	A	B	B	A	A	C	C	D	C	B	A	B	A	A	D	D	C	B	A	A	A	A	C	C		C	B	C	A		
Acetic Anhydride	B	A	A	B	B	A	A	C	D	B	D	D	D	D	A	D	D	D	D	A	A	A	A	A	D	A	C	B	B	C	A		
Acetone6	A	A	A	B	A	A	A	A	A	A	A	D	D	D	A	D	B	A	D	C	B	A	A	A	A	D	D	B	C	A	D	B	
Acetyl Chloride		C	A					D							A								A		A						A	A	
Acetylene2	A	A	A	A	A	B		B		A	A		B				A	A			D	A	A	A	A	A	C	B	A	C	A		
Acrylonitrile	A	A	C		B	B	B	A		C							B		D		B	A	A	A	C	D		D	D		A		
Alcohols: Amyl	A	A	A	C	A	A	A	B	C	C	C	A	A	B	A	C	A	A	B	B	B	A	A	A	A	A	D	A	A	C	A		
Benzyl		A	A		B	A	A	A	C				D	B		A	A	A	D	D	A	A	A	A	A	D		B	B	D	A		
Butyl	A	A	A		B	B	A	B	C	C	C	A	A	B	A	A	A	A		B	B	A	A	A	A	A	D	A	A	A	A		
Diacetone2		A	A		A	A	A	A	C		A		D			A	A	A			D	A	A	D	D		D	A	D	A	A		
Ethyl		A	A	A	B	A	A	A	C	A	A		A	C			A	B	A	B	B	A		A	A	A	A	B	A	B	A	A	
Hexyl		A	A		A	A	A	C		A						A	A	A			A	A	A	A	A	A	D	B	A	A	A	A	
Isobutyl		A	A		B	A	A	A	C		A					A	A	A	B		A	A	A	A	C	B	A	A	A	A	A	A	
Isopropyl		A	A		B	A	A	A	C	C	A					A	A	A			A	A	A	A	C	C	B	A	A	A	A	A	
Methyl6		A	A	A	B	A	A	A	C	A	A		B		A	A	C	A	D	B	A		A	A	C	B		A	A	A	A	A	
Octyl		A	A		A	A	A	A	C		A					A	A	A					A	A	A	B		B	A	C	A	A	
Propyl		A	A		A	A	A	A	C		A					A	A	A					A	A	A	A	B	A	A	A	A	A	
Aluminum Chloride 20%		D	C	D	B	A	A	D		D	A		A	B		A	C	A		B	A	A	A	A	A	A	A	A	A	A	A	A	
Aluminum Chloride		C	D	C		D	C	A	C		D	B	A	A	A	A	A	D			A	A	A	A	A	A	C	A			A		
Aluminum Fluoride		D	C	D		D	B				A	A	A		A	A	C	D		B	A		A	A	A	C	A		C	A	A		
Aluminum Hydroxide6		A	A	A	A			A		D	A		A	A	A	B	A			A	A	A	A	A	A	A	A	A	A	A	A	A	
Aluminum Potassium Sulfate (Alum), 10%		A	A		A	B				D	A		A	A	A	A	A			A	A	A	A	A	A	A	A	A	A	A	A	A	
Aluminum Potassium Sulfate (Alum), 100%		D	A	B	B	B	C			A		A	B	A	A	C	D		B	A	A	A	A	A	A	A	A	A	A	A	A	A	
Aluminum Sulfate		C	C	A	A	A	A	C	C	D	A		A	A	B	A	A	C	A		B	A	A	A	A	A	A	A	A	A	A	A	
Amines		A	A	A		A	B	A	B		A	B		C	A	A	B	D	A					A	A	D	D	C	B	B	C	A	
Ammonia 10%			A			A	A					D	A		A	A	A				A	A		A	A	D		A			B		
Ammonia, Anhydrous	A	B	A	A	B	B	A	D		D	B	D	A	B	A	A	D	A		B	A	B	C	A	D	B	B	A	A	D	A		
Ammonia, Liquids		A	A	A	D		B	D		A	A		A	B	A	A	D			D	A		A	A	A	D	B	B	A	A	D	A	
Ammonia, Nitrate		A	A	A	C			D		A		B	B		A	C					A	A	A	A	A	A	C			A	A		
Ammonium Bifluoride		C	A		D		B						A		A	D					A		A	A	A	A					A		
Ammonium Carbonate	B	A	A	A	C	A	B	B		C	B		A	B	A	A	D	A			A		A	A	B	D	C	A	A		A		
Ammonium Casenite			A													A	D														A	A	
Ammonium Chloride	C	A	C	A	C	D	A	D	C	D	D	A		A	B	A	A	B	A		B	A	A	A	A	A	A	C	A	A	A	A	
Ammonium Hydroxide	A	A	A	A	C	A	A	D	D	A	C		A	B	A	A	D	A	B	B	A	A	A	A	B	B	B	A	A	C	A		
Ammonium Nitrate	A	A	A	A	B	A	A	D	D	A	D		A	B	A	A	C	D		B	A	A	A	A	D	A	C	A	A	A	A	A	
Ammonium Oxalate		A	A	A			A				A						B						A		A	A					A		
Ammonium Persulfate	A	A	A	C	C	A	A			D	A	D	A		A	A	D	D			A		A	A	C	A	A	A	A	A	A	A	
Ammonium Phosphate, Dibasic	B	A	A	A	B	A	A	C			D		A		A	A	B	A		B	A		A	A	A	A	B	A	A	A	A	A	
Ammonium Phosphate, Monobasic		A	A	A	B	A	A	D			A		A	A	A	A	B	A		B	A		A	A	A	A	B	A	A	A	A	A	
Ammonium Phosphate, Tribasic	B	A	A	A	B	A	A	C		C	D		A		A	A	B	A		B	A		A	A	A	A	B	A	A	A	A	A	
Ammonium Sulfate	C	D	B	A	B	A	A	B	C	C	C	A		A	D	A	A	B	D		B	A	A	A	A	D	A	B	A	A	A	A	
Ammonium Thio-Sulfate			A			A				D	A						B							A	A	A	A				A	A	
Amyl-Acetate	B	A	A	C	B	A	A	C			C	C	D	D	A	D	A	B		D	D	A	A	A	D	D	D	D	A	D	A	A	
Amyl Alcohol		A	A		B	A	A	A			A	A	A	B	A	C	A	A		B	A		A	A	B	B	D	A	A	C	A	A	
Amyl Chloride		C	B		D		A	A			A	A	D	C	A	D	A	C		D	D		A	A	A	D		D	D	D	A	A	
Aniline	B	A	A	A	C	A	B	C			C	C	D	D	A	D	D	C		D	C	B	A	A	A	C	D	C	D	B	D	A	
Antifreeze		A	A		A	A	B	B	B	C			A	B	A	A	A	A	B	B	A	A	A	A	A	A	C	A	A	A	A	A	A
Antimony Trichloride		D	D		D	C	A						A	A	A		D			B	A		A	A	A	A	C	A	A	A	A	A	
Aqua Regia (80%, HCL, 20%, HNO)		D	D		D	A	D	D			C	D	D	A	D	D	D			D	C			D	C	D	C	D	D	D	D	D	
Arochlor 1248											A						D						A		A	D		D	B	D	A	A	

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315

P.O. Box 529, Mordialloc, Victoria, 3195

102-104 Malcolm Road, Braeside, Victoria, 3195

Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3806)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy	
Aromatic Hydrocarbons		A	A										D						C						D	D	D	D	A			
Arsenic Acid	B	A	A	D			D	B	D	D	A	A	B	A	A	D	A		B	A			A	A	A	A			C	A		
Asphalt		B	A	C			A	C				A							A	A			A	A	B	C	B	D	D	A		
Barium Carbonate	B	A	A	B	A	A	B		B	B		A	A	A	A	A			B	A			A	A	A	A			A	A		
Barium Chloride	C	D	A	A	D	A	A	B			C	A	A	B	A	A	B		B	A	A		A	A	A	A	B	A	A	A		
Barium Cyanide			A				C		A							B			B				A	A	C		A	A		A		
Barium Hydroxide	B	C	A	A	D	B	B	B		C	C	A	A		A	A	D	A		B	A	A		A	A	A	C	A	A	A		
Barium Nitrate		A	A		A	D	A	A		A	A	B			A	A							A	A	A	A	A	A		A		
Barium Sulfate	B	A	A	A	D	A	A	C		C	C	A	A		A	A	A		B	A	A		A	B	A	A	D	A	A	B		
Barium Sulfide	B	A	A		D	B		C		C	C		A	A	A	A	A		B	A			A	A	A	A	C	A	A	A		
Beer2	A	A	A		A	A	A	A	B	D	D	A	A		A	A	B	D	B	B	D		A	A	A	D	C	A	A	A		
Beet Sugar Liquids	A	A	A		A		A	B	A				A		A	A	B	A	B		A		A	A	A	A	B	A	A	A		
Benzaldehyde3	A	A	B	B	A	A	A	B	A	B	A	C	D	D	C	A	D	A	C	D	D	D	A	A	A	D	B	D	A	D		
Benzene2	B	A	A	A	B	A	B	B	A	B	C	B	D	C	A	D	A	A	D	D	D	A	A	A	A	A	D	D	D	A		
Benzoic Acid2	B	A	A	A	B	A	A	B		D		A	A	B	A	A	B	D		B	D		A	B	A	D		D	D	A		
Benzol		A	A		B	A	A	B	A				D		A	D	A	A					A	A	A	D	D		D		A	
Borax (Sodium Borate)		A	A	A	C	B	A	A	B	A	C	A	A	A	A	A	A		B	A	A		A	A	A	A	B	C	A	A	C	A
Boric Acid	B	A	A	A	B	A	A	B	C	D		A	A	B	A	A	A	A		B	A		A	A	A	A	A	A	A	A	A	
Brewery Slop			A				A		A								A						A	A	A	A	A	A		A	A	
Bromine2 (wet)	D	D	D	D	D	A	A	C		D	D	A	B	B	A	D	D	D	D	D	D	D	D	D	A	A	D	D	D	D	C	
Butadiene	A	A	A		A		C	A	C	C	A	A			A		A	A					B	A	A	A	A	B	A		A	
Butane2 1	A	A	A		A	A	C	C	A	A	C	A	C	A	D	A	A	B	C	D	A	A	A	A	A	D	B	D	D	A		
Butanol		A	A		A	A							A																			
Butter		B	A		A		D		D				B		B	A		B					A	A	A	A	B	A	D	A		
Buttermilk	A	A	A	A	A		D		D			B	A	A	A	A	B						A	A	A	A	A	A	D	A		
Butylene	A	B	A		A		A	A	A	A		B		A		A							A	A	A	A	B		D	D	A	
Butyl Acetate1		C		A		A	A		A	C	D	D	A	D	A				C	D	A		A	A	D	B	D	D	B	D	A	
Butyric Acid1	B	B	A	A	B	A	A	C		D		A	B	A	A	A	C	D	D		A		A	D	D	D	D	B	A		A	
Calcium Bisulfate	C	D	A		D		D	D				A	A	A			A							A	A	C	C		A	A		
Calcium Bisulfide		B		C	A	A	C						A		A	A	D	A		B	A		A	A	A	A	A	D		A		
Calcium Bisulfite		B	A		C	A	A	C					A		A	A	A						A		A	A	A	A		A		
Calcium Carbonate	B	A	A	A	C	A	A	C		D			A	A	A	A	A		B	A			A	A	A	A	A	A	A	A	A	
Calcium Chlorate		B	A		B	B	C						A	A	A	A			A	A			A	A	A	A	A	A	A	A	A	
Calcium Chloride	C	A	D	C	C	A	A	B		C		A	A	A	A	D	A	B	B	A	A		A	A	A	A	B	D	A	A	A	
Calcium Hydroxide	B	A	A		C	A	A	B					A	A	A	A	B	A		B	A		A	A	A	A	C	A	A	A	A	
Calcium Hypochlorite	D	D	C	C	C	A	B	D		D		A	D		A	A	D	D		B	A		A	A	A	B	C	D	A	C	A	
Calcium Sulfate	B	A	A	A	B	A	B	B					A	A	A	A	A	C	B	A	A		A	A	A	A	A	D		C	A	
Calgon		A	A				C	D							A	B							A	A	A	A	A	A		A	A	
Cane Juice2		A	A		B		B	C	A				A										D	A	A	A	A	A	A	A	A	
Carbolic Acid (See Phenol)																																
Carbon Bisulfide2	B	A	A	A	A		C	B				D	D			A	A					D	A	A	A	D	D	D	D	A		
Carbon Dioxide (wet)		A	A		C		A	C	C	C					A									A	A							
Carbon Disulfide2		B	A		C		C	C	B	C			D	C	A	D	A	A		D	D	A	A	B	A	D	D	D	D	A		
Carbon Monoxide		A	A		A								A			B	A	A		B	A		A	A	A	A	B	B	A	C	A	
Carbon Tetrachloride2 1	B	B	B	A	C	A	A	C	A	C	D	A	C	C	A	D	A	A	D	D	D	C	A	A	A	C	C	D		D	C	
Carbonated Water	B	A	A	A	A		B	D					A			A	A	A		A			A	A	A	A	A	A	A	A	A	
Carbonic Acid	B	A	B	A	A		A	B		D		A	A		A	A	A		B	A			A	A	A	B	B	A	A	A	A	
Catsup		A	A	A	D		C	D					A		A	B	A	B		A			A	A	A	A	A	C	A		A	
Chloracetic Acid2	D	D	D	D	C	A	A	D		D		D	A	D	A		D	D		D	D		A	A	D	D	D	B	D	B	A	
Chloric Acid		D	D										D		A												D		D		D	
Chlorinated Glue		A	A		D		C	D								C		C	D					A	A	C	D	B	D	A		
Chlorine, Anhydrous Liquid		D	D	D	D	D	A	D		C			D	B	A	A	D	D		D	D	C	A	D	A	D	D	B	D	B		
Chlorine (dry)	B	A	A	A	D	D	A	A	B	A					A								C	A	A	D		D		D		
Chlorine Water	D		D		D	A	B	D	D	D			A	A		A	C		D			D	C	C	A	A	D	C	D			
Chlorobenzene (Mono)	A	A	A		B		A	B		B	C	A	D	D	A	D	A	A	D	D	D	D	A	A	A	A	D	D	D	D	A	
Chloroform	A	A	A	A	D	A	A	B		D	C	C	D	C	A	D	A	C	D	D	D	C	A	A	A	D	D	D	D	D	A	

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315  
 P.O. Box 529, Mordialloc, Victoria, 3195  
 102-104 Malcolm Road, Braeside, Victoria, 3195  
 Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3806)	Teflon	Noryl	Polyacetal	Nylon	Cycloc (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy	
Chlorosulfonic Acid1	D	D	D	D	A	B	D			D	D	C	C	A	D	D	D	D	D	D	D	C	D	D	D	D	D	D	D	C		
Chlorox (Bleach)		A	A	C		A	A			D	C		A	B	A	A	D	D	B		D	C	A	A	A	C		B	B	D	A	
Chocolate Syrup		A	A	A						D					A	A	A			A		A	A	A	C			A	A	D	A	
Chromic Acid 5%		A	A	B	C	A	A	D	D	D			A	B		C	D	D	B	B	A	A	D	C	A	D	C	D	A	B	B	
Chromic Acid 10%		B				A	A	D				A	A		A	A	D			A		A	A	D			D			D	C	
Chromic Acid 30%		B				A	A	D				B	A		A	D	D			A		A	A	D			D			D	D	
Chromic Acid 50%		C	B	B		C	A	A	D	D	D	C	B	B	A	D	D	D	C	C	B	B	D	A	A	D		D	A	D	C	
Cider		A	A	A	B		A	D				A			A	B			B		A	A	A	A			A	A	A	A	A	
Citric Acid		A	A	A	C	A	A	D	C	D		A	A		A	A	B	C	C	B	B		A	A	A	D	C	A	A	A	A	
Citric Oils		A	A		C		B								A	B				A		A	A	A	A	C	D			A	A	
Coffee		A	A	A	A		B		C						A	A	A	A		A		A	A	A	A			A	A	A	A	
Copper Chloride		C	D	D	B	D	A	A	D		D	A	A	B	A	A	B	D		B	A	A		A	A	A		A	A	A	A	
Copper Cyanide		A	A	A	D	A	A	C	D		D	A	A		A	A	B	A		B	A	A	A	A	B	B		A	A	A	C	
Copper Fluoborate		D	D			B	D	D					A	A	B					A		A		A	B	A	B	A	A	A	A	
Copper Nitrate		B	A	A	B	D	A	A	D			A	A		A	A	B	D		B	A		A	A	A	A		A		A	A	
Copper Sulfate (5% Solution)		A	A	A	D	A	A	D	D	D		A	A		A	A	B	D		B	A	A	A	A	A	A	C	A		C	A	
Copper Sulfate		B	B			A	A	C	D			A	A		A	A	C			A		A	B	B		A	A			A	A	
Cream		A	A		A		C	D							A	A	A	A		A		A	A	A	A		A	C	A		A	
Cresols2		A	A		B		D	C					D	D			D		D	D	C	A	A	A	A	D	D	D	D	D	A	
Cresylic Acid		B	A	A		C	A	B	C			B	B	D	A		D	D		C			A	A	A	D		D	D	D	A	
Cyclohexane		A			A	A		A			A			D		D	A			D	A	A	A	A	A	A	D	D	D	D	A	
Cyanic Acid		A														D										C	D			A	A	
Cycolic Acid							A						A		A	C				B	A	A	A		A	A	A	A	A	A	A	
Detergents		A	A		A		A			A		A				A	B	A	B	B	A	A	A	A	A	A	A	B	A	C	A	
Dichlorethane		A	A				A					D	D	A			A		D					B			D			A	A	
Diesel Fuel		A	A	A		A		A	A						D	A				D	A	A	A	A	A	A		D	D	D	A	
Diethylamine		A	A			A						D		A	B	D				C		A	A	D	B		B	B	C	A	A	
Diethylene Glycol		A					A								A	A	B	B			A	A	A	A	C	A	C	A	A	A	A	
Diphenyl Oxide		A					A									A					A	A	A	D		A	D	D	D	D	A	
Dyes		A	A		B		C								A	A								A			C			A	A	
Epsom Salts (Magnesium Sulfate)		B	A	A	A	A	A	B	B				A			A	A			A		A	A	A	A	A	A	A	C	A	A	
Ethane		A	A			A									D	A							A	A	A	A		B	D	D	A	
Ethanolamine		A	A							C						D					A	A	A	D	B	C	B	C	A		A	
Ether3		A	A	A	A		B	B	A		B	D	C		D	A	C				A	A	A	C	D		D	C	D	A	A	
Ethyl Acetate2		A	A		B		B	B			C	D	D	D	A	D	A	A	D	C	C	A	A	A	D	D	C	D	B	D	A	
Ethyl Chloride		A	A	A	B	A	B	B		C	D	A	D	D	A	D	A	A		D	D	A	A	A	A	D	D	C	A	A	A	
Ethyl Sulfate		D														B							A	A	A	A				A	A	
Ethylene Chloride2		A	A		C	B	B	A		C	C		D		A	D	A		D		D	A	A	A	A	D	D	D	C	D	A	
Ethylene Dichloride		A	A		D	A	B	C			C		D	D	A	D	A	A		D	A	A	C	A	A	D	D	D	C	D	A	
Ethylene Glycol4		A	A		A		A	B	B	B	C	A	A	B	A	A	A	A	B	B	A	A	A	A	A	A	C	A	A	A	A	
Ethylene Oxide		A	A				A						D		A	A	A	A					A	A	D	D	D	D	C	D	A	
Fatty Acids		A	A		B	A	A	C		D		A	A	B	A	B	A	A		B	A		A	A	A	C	C	B	C	C	A	
Ferric Chloride		D	D	D	D	A	B	D	D	D		A	A	B	A	B	D		B	A	A	A	A	A	C	C	B	C	C	A	A	
Ferric Nitrate		A	A	A	D	A	A	D					A	A		A	B	D		B	A	A	A	A	A	A	D	A	A	A	A	
Ferric Sulfate		A	C	A	D	A	A	D	D	D		A	A	B	A	A	B	A	C		A	A	C	A	A	B	C	A		A	A	
Ferrous Chloride		D	D		D	A	B	C		D		A	A	B	A	A	B	D		B	A	A	A	A	A	B	C	A		A	A	
Ferrous Sulfate		B	A	C		D	A	B	C		D	D	A	A	B	A	A	B	D		B	A	A	A	A	B		A		A	A	
Fluoboric Acid		D	B			D	A		D		D	A	A	B	A	B	B	C		B	A		A	A	D	A	B		A	A		
Fluorine		D	D	D	D	A	A	D		D	D		C	C		C				D	C		D							D	A	
Fluosilicic Acid			B		D	D	B			D		A	A	B	A	A	B	D		B	A		A	D	B	A		A		C	A	
Formaldehyde 40%			A				A					B	B		A	A	D					A	A		A	D	B	B	A		A	
Formaldehyde		A	A	A		A	A	B	A	B	D	A		A	B	A	D	A	A		B	A	A	A	A	D	C	B	D	B	C	A
Formic Acid6		C	A	B	B	D	C	A	C	C	D	D	A	D	B	A	A	D	D		B	A	A	A	A	B	D	C	D	A	C	B
Fruit Juice		A	A	A	A	B		C		D	D	A		A	D	A	B	A		B	A		A	A	A	A	D	C	A		A	A
Fuel Oils		A	A	A		A	A	A	B		C	B	A	A		A	A	A		D	B	A	A	A	A	A	C	B	D	D	A	A
Furan Resin		A	A			A				A	A				A		A						A		A	A	D		D		D	A

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315  
 P.O. Box 529, Mordialloc, Victoria, 3195  
 102-104 Malcolm Road, Braeside, Victoria, 3195  
 Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3806)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPDM)	Rubber (Natural)	Epoxy
Furfural1	A	A	A	A	A	B	A			A	D	D		A	D	B	A	D	D	D	A	A	A	D	D	D	D	D	B	D	A
Gallic Acid	B	A	A	A	A	A	A		D	D			A	A	A		A								B	A					
Gasoline1 4	A	A	A	A	D	A	A	A	A	A	C		A	D	A	A	D	D	C	A	A	A	A	A	A	D	D	C	D	A	
Gelatin	A	A	A	A	A	A	C	D	D	A	A	A	A	A	A	A				A	A	A	A	A	A	A	A	A	A	A	
Glucose	A	A	A	A	A	A	B	B	B	A	B	A	B	A	B	A	B	B	A		A	A	A	A	B	A	A	A	A	A	
Glue P.V.A.1	B	B	A	B	A	A				A	A	B	A			A	A						A	A	A	A				A	
Glycerine	A	A	A	A	A	A	A	B	B	B	A	A	B	A	A	A	A	C		A			A	A	A	A	B	A	A	A	
Gold Monocyanide			A					A	D							A							A	A	A	A	A	A	A	A	
Grape Juice		A	A	B			B	D					A			A	B	B					A	A	A	A	A	A	A	A	
Grease4	A	A	A	A			B	A	A				A			A	A						A	A	A	A	D			A	
Heptane1	A	A	A	A	A	A				B	A	A	A	D	A	A	C	D	D	A	A	A	A	A	A	A	B	D		A	
Hexane1	A	A	A	A	A	B				B	A	C	A	D	A	A	D		C	A	A	A	A	A	A	B	B	D	D	A	
Honey	A	A	A	A	A	A	A	A	A			A			A	A	A	B					A	A	A	A	A	A	A	A	
Hydraulic Oils (Petroleum)1	A	A	A	A			B	A	A					A	A	A				D	A	A	A	A	A	B	D	D	D	A	
Hydraulic Oils (Synthetic)1	A	A	A	A			A	A								A	A			D			A	A	A	C	D			A	
Hydrazine	A	A							C							D							A	A	B	D	B	A	C	A	
Hydrobromic Acid 20%			D			A	A					A	A	A	A	D				A			B	A	D	C				B	
Hydrobromic Acid4	D	D	D	D	A	A	D		D	D	A	A	B	A	C	D	D		B	B			A	A	A	D	D	D	A	A	
Hydrochloric/Muratic Acid (Dry gas)	D	C	A	D	A				D			A	A										A							A	
Hydrochloric/Muratic Acid (20%)4		D	D	D	C	B	D		D		A	A	B	A	A	D	D	B	A	A	D	A	A	A	C		C	A	C	A	
Hydrochloric/Muratic Acid (37%)4		D	D	D	C	B	D		D		A	A	B	A	A	D	D	C	A	A	D	A	C	A	C	C	C	C	D	A	
Hydrochloric/Muratic Acid (100%)		D	D	D	D	C	D		D		A	A	A			D		A				A	C	C	D	C			A	A	
Hydrocyanic Acid	A	A	C	A	A	A	D	D		C	A	B	A	A	B	A			B	A			A	A	A	C		B	A	A	
Hydrocyanic Acid (Gas 10%)		D	D										A	A														C	A	C	A
Hydrofluoric Acid (20%)1		D	D	D	D	B	D		D		D	B	A	A	D	D			C	A	C	B	C	A	D		C	A	C	B	
Hydrofluoric Acid (75%)1 2		C	D	D	D	C	D		D		A	C	B	A	D	D	D		C	B	C	D	D	A	D	D	D	C	C	C	
Hydrofluoric Acid 100%		D	D	D	D	B	D		D	D		C	D	A					D		C	D	D		D		D		D	A	
Hydrofluosilicic Acid (20%)		D	D	D	D	B	A	D		D		D	A	B	D	D			A		A	D	A	B		B	A	A	A	C	
Hydrofluosilicic Acid		D	D	C	C	D							C	A									A				D	A			
Hydrogen Gas	A	A	A	A			A	B	B	A	A		A											A						A	
Hydrogen Peroxide 10%		C	C	A	C	A	D	D	D			A	A	A			D		A		B	A	A		A	D	C		B		
Hydrogen Peroxide 30%			B		B	A	D					A	A			D				A	C			A	D	C			B		
Hydrogen Peroxide	A	B	A	A	B	A	D	D	D	C	A	C	A	B	D	D			B	A	C		A	A	D	C	D	C	C	A	
Hydrogen Sulfide, Aqueous Solution		D	A	C	C	A	A	D	C	D		A	B	A	A	D	D		B	A	A	A	A	A	D	C		B	A	D	A
Hydrogen Sulfide (dry)	A	C	A		D	A	D	C	B	B		A	A			D						A		A	D					A	A
Hydroxyacetic Acid (70%)				D	B								A			D							A	A	A	A		A	A	A	
Ink	A	A	A	C				D	D						B	A	A		B				A	A	A	A				A	
Iodine		D	D	D	A	B	D		D		D	B	A	A	C	D	D	D	D	D		D	A	A	B		D	B	D	A	
Iodine (In Alcohol)			B		D	A						D	A	A	C	D				B			A	A	A	D				D	
Iodoform	B	C	A		A		C	C	B				A			A								A							
Isotane2					A										D	A				D			A	A	A					D	A
Isopropyl Acetate			B	C												A							A	A	D	D	D	B	D	A	
Isopropyl Ether2	A	A	A	A		A				A				A	D	A				D			A	A	D	B	D	D	D	A	
Jet Fuel (JP#, JP4, JP5)	A	A	A	A		A	A	A	A	A	A	A	A	A	D	A	A			D	A	A	A	A	A	D	D	D	D	A	
Kerosene2	A	A	A	A	A	A	A	A	A	B	A	A	A	D	A	D	A	A	B	D	D	A	A	A	A	A	D	D	A	D	A
Ketones	A	A	A	B	A	A	A		A	A	D	D	D	A	D	B	A		D	D	A	C	A	D	D		D	D	C	C	
Lacquers	A	A	A	A		A	C	C	C				D		C	A	A					A	A	A	D	D	D		D	A	
Lacquer Thinners			A		A	A	C					C	A	D	A					B			A	D			D	A			
Lactic Acid	A	A	B	C	C	A	A	D		D	D	C	A	B	A	A	B	C		B	A	A	A	A	B	B	A	B	A	A	
Lard	B	A	A	A	A		A	A	C		A					A	A	C		A			A	A	A	A	C	B		D	A
Latex		A	A	A		A										A	A	A		B				A	A	A	C	A		A	
Lead Acetate	B	A	A		D	A	A	C			D	A	B	A	A	A	A		B	A			A	A	D	B	D	A	A	A	
Lead Sulfamate																A							A		A	B	C	A	D	C	A
Ligroin3			A			A									D	A				D				A	A	A	B	A	D	A	A
Lime		A	A	C	A	A	A					A			A	D		C					A	A	A	A	C	B	D		A
Lubricants	A	A		A	A	A	B					A	A			A	A	B				A	A	A	A	A	C	D		D	A

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315  
 P.O. Box 529, Mordialloc, Victoria, 3195  
 102-104 Malcolm Road, Braeside, Victoria, 3195  
 Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3806)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPDM)	Rubber (Natural)	Epoxy										
Magnesium Carbonate	A	A	A				B						A			A	A			B	A		A	A	A	A	A	A	A	A	A										
Magnesium Chloride	B	B	B	A	D	A	A	B	C	D	C		A	B	A	A	A	A		B	A	A		A	A	A	A	A	A	A	A	A									
Magnesium Hydroxide	A	A	A	D	A	A	C	B	B	B	B	A	A	A	A	A	A		B	A	A	A		A	A	A	B	B	C	A	A										
Magnesium Nitrate	A	A	A		A	A							A		A	A	A			B	A			A	A	A	A				A	A									
Magnesium Oxide	A	A															A							A	A	A	A	A	A	A	A	A									
Magnesium Sulfate	B	B	A		B	A	B	B	B	C	B		A	B	A	A	A	A		B	A	A		A	A	A	A	A	A	D	C	A									
Maleic Acid	C	A	A	A	B	A	A	C			B		A	B	A	A	C	A			C			A	A	A	D	A	D	D	A	A									
Maleic Anhydride						A											C							A	A	A	D	D	D	D	A	A									
Malic Acid	B	A	A		C	A	D				D		A		A			A						A	B			A	A	A	A	A									
Mash		A	A					A									A	A						A	A		A					A	A								
Mayonnaise	A	A	A		D			D		D	D				A	A	A	A	B		A			A	A	A	A						A	A							
Melamine		D	D					D									D							A	A		C							A	A						
Mercuric Chloride (Dilute Solution)	D	D	D	D	D	A	B	D	D	D	D		A	A	A	A	A	A		B	A			A	A	A	A	A	A	A	A	A	A	A							
Mercuric Cyanide	A	A	A		D	A		D			D		A		A	A	A			B	A			A	A	A	A							A	A						
Mercury	A	A	A	A	C	C	A	D	D	A	A		A		A	A	A	A		B	A			A	A	A	A	A	A	A	A	A	A	A	A						
Methanol (See Alcohol Methyl)																																									
Methyl Acetate	A		A		A	A					B				A				A		D			A	A	D	D	D	B	B	D	D	D	D							
Methyl Acrylate																									A	A	D	D		B	B	D	A	A	A						
Methyl Acetone	A		A		A			A		A	A				A	D	A								A	D	D	D	D	D	D	D	D	D	C	C					
Methyl Alcohol 10%	A		A		C		A	C			B		A		A			A										B						A	A						
Methyl Bromide																		A		D				A	A	A	B		D	D	D	D	D	D	B						
Methyl Butyl Ketone			A		A												D	B						A	A	D	D	C	D	A	D	D	D	D	B						
Methyl Cellosolve					A			A									C	B			A			A	A	D	D	D	D	D	D	D	D	D	D	C					
Methyl Chloride	A	A		D	A	A	A					A	D		A	D	A	A		D	D			A	A	A	D	D	D	D	D	D	D	D	D	A					
Methyl Dichloride																	D	A						A	A	A	D		D	D	D	D	D	D	D	A					
Methyl Ethyl Ketone	A	A		A	A	A	A					D	D		A	D	B	A	D	D	A	A		A	A	A	D	D	C	D	A	D	D	D	B						
Methyl Isobutyl Ketone2			A			A	A					D	D		A	D	B	A	D		C	A		A	A	A	D	D	C	D	C	D	D	D	B						
Methyl Isopropyl Ketone			A													D	B	A						A	A	D	D	B	D	B	D	D	D	D	B						
Methyl Methacrylate																								A	A	D	D	D	D	D	D	D	D	D	D	A	A				
Methylamine	A		A		A			D		B	B						B	D						A	A		B								A	A					
Methylene Chloride	A	A	A		A	A	A	A	C		B	D	D		A	D	A	D		D	D			A	A	D	D		D	D	D	D	D	D	D	A					
Milk	A	A	A	A	A			C	C	D	D		A				A	A	A	B	B	A		A	A	A	A	B	A	A	A	A	A	A	A	A					
Molasses	A	A	A	A	A			A	B	A	A		A				B	A	A		B	A		A	A	A	A	A	A	A	A	A	A	A	A	A					
Mustard	A	A	A	A	B			B	C	B	A						B	B	A	B				A	A	A	A	B	C	C						A	A				
Naphtha	A	A	A	A	A	A	A	B		B	B	A	A	C	A	D	A	A	C	D	A	A		A	A	A	A	B	D	D	D	D	D	D	D	A	A				
Naphthalene	B	A	B		B	A	A	C		B	A	A	D		A	D	A			D	B	A		A	A	A	B	D		D	D	D	D	D	D	A	A				
Nickel Chloride			A	B		D	A	A	D		D		A	A	B	A	A	B	A		B	A		A	A	A	A	A	A	A	A	A	A	A	A	A	A				
Nickel Sulfate	B	A	B		D	A	B	C	C	D	D	A	A	A	A	A	B	A		B	A			A	A	A	A	A	A	A	A	A	A	A	A	A	A				
Nitric Acid (10% Solution)	A	A	A	A	D	A	A	D		D	D	A	A	A	B	A	A	D	D	C	B	A	D	C	B	A	D		D	B	D	D	D	D	D	A	A				
Nitric Acid (20% Solution)			A	A	A	D	A	A	D		D		B	A	B	A	A	D	D	D	B	A	C	D	C	A	D		D	D	D	D	D	D	D	D	B				
Nitric Acid (50% Solution)			A	A	A	D	A	A	D		D		B	A	B	A	A	D	D	D	C	D	C	D	A	A	D		D	D	D	D	D	D	D	D	D				
Nitric Acid (Concentrated Solution)			D	B	A	B	A	B	D	D	D		D	C	A	D	D	D	D	D	D	D	D	D	C	D	A	B	D		D	D	D	D	D	D	D				
Nitrobenzene2	B	A	B		C	A	B	D		B	B	D	D	D	A	D	B	C	D	D	C	B	A	A	A	B	D	D	D	D	D	D	D	D	D	D	B				
Oils: Aniline	A	A		A	C	A	D	A		A			D		A	D	D	C	D		A			A	A	A	D		D	D	D	D	D	D	D	D	A				
Anise	A	A																						A	A												A	A			
Bay	A	A																						A	A	A											A	A			
Bone	A	A																						A	A	A	A											A	A		
Castor	A	A		A				A		A														A	A	A	A											A	A		
Cinnamon	A	A																						A	A	A	D												A	A	
Citric	A	A						D		D									A	A				A	A	A	A											A	A		
Clove	A	A																						A	A		A												A	A	
Coconut	A	A		B				A		A														A	A	A	A												A	A	
Cod Liver			A	A		B																		A	A	C	A												B	A	
Corn			A	A	A	B				B		A												A	A	C	A													D	C
Cotton Seed	B	A		A	A	B				B		A	C										A	A	C	A														D	C
Creosote2	A	A		A																				D			D													B	D

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315

P.O. Box 529, Mordialloc, Victoria, 3195

102-104 Malcolm Road, Braeside, Victoria, 3195

Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3806)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPDM)	Rubber (Natural)	Epoxy
Diesel Fuel (2D, 3D, 4D, 5D)	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A	A	A	A	A	A	D	D	D	A		
Fuel (1, 2, 3, 5A, 5B, 6)	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	B	A	A	A	A	B	D	D	D	A		
Ginger	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A		
Hydraulic (See Hydraulic)	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A		
Lemon	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A	D	A	A	A	A		
Linseed	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	C	A	A	A	A	A	A	A	D	D	D	D	A		
Mineral	A	A	A	A	A	A	A	A	B	A	A	A	A	A	B	A	A	B	A	A	A	A	A	A	B	D	D	D	A		
Olive	A	A	A	A	A	A	A	B	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	C	B	D	D	D	A		
Orange	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A		
Palm	A	A	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A		
Peanut3	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	D	A	A	A	A	A		
Peppermint2	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	D	D	A	A	A	A	A		
Pine	A	A	A	A	A	A	D	C	B	A	A	A	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A		
Rape Seed	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	D	D	D	D	D	A		
Rosin	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A		
Sesame Seed	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A		
Silicone	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A		
Soybean	A	A	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A		
Sperm	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A		
Tanning	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A		
Turbine	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	A	D	D	D	D	D	D	A		
Oleic Acid	B	A	A	B	B	B	B	C	C	C	C	A	C	A	C	B	A	B	D	C	A	A	D	B	D	D	D	D	A		
Oleum 25%	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	D	D	D	D	D		
Oleum	B	A	B	C	C	B	D	D	A	D	A	D	A	D	A	D	A	D	D	A	A	C	D	D	D	D	D	D	A		
Oxalic Acid (cold)	C	A	B	A	C	C	B	B	C	D	D	A	B	A	C	C	D	A	A	A	A	A	B	C	B	A	C	A	A		
Paraffin	A	A	A	A	A	A	A	B	B	A	A	A	B	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A		
Pentane	A	C	C	A	B	A	B	B	A	A	A	A	D	A	A	D	A	A	A	A	A	A	B	D	D	D	D	D	A		
Perchloroethylene2	B	A	A	A	C	B	B	A	A	A	D	A	D	A	D	D	A	A	A	A	C	D	D	D	D	D	D	D	A		
Petrolatum	A	A	B	B	C	C	A	D	A	A	B	A	D	A	A	B	A	A	A	A	A	A	A	B	A	D	A	A	A		
Phenol 10%	B	A	A	A	B	C	B	D	A	C	A	A	A	A	A	D	A	A	A	A	A	B	D	C	D	C	C	C	C		
Phenol (Carbolic Acid)	B	A	A	A	B	C	A	B	D	D	D	A	A	C	A	C	D	D	D	B	A	A	D	A	D	D	D	D	B		
Phosphoric Acid (40% Solution)	B	A	A	D	A	A	D	D	D	A	B	A	A	D	D	C	B	A	A	B	C	A	D	D	B	C	A	A	A		
Phosphoric Acid (40% - 100% Solution)	C	B	B	D	B	A	D	D	D	A	B	A	A	D	D	D	C	A	A	B	D	A	D	D	B	C	C	A	A		
Phosphoric Acid (Crude)	D	C	D	C	A	D	D	D	A	A	A	A	A	D	D	D	C	A	C	D	A	D	D	D	B	A	A	A	A		
Phosphoric Anhydride (Dry or Moist)	A	A	A	A	A	A	D	D	A	D	D	A	A	A	A	A	A	A	A	A	A	A	D	D	D	A	A	A	A		
Phosphoric Anhydride (Molten)	A	A	D	A	A	D	D	D	A	A	A	A	A	A	A	A	A	A	D	A	A	A	D	C	D	D	D	A	A		
Photographic (Developer)	C	A	C	C	A	A	A	D	A	A	A	A	C	A	A	C	B	A	A	A	A	A	A	A	A	A	A	A	A		
Phthalic Anhydride	B	A	B	B	A	B	C	C	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	A		
Picric Acid	B	A	A	C	A	D	D	D	D	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A		
Plating Solutions																															
Antimony Plating 130° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	B		
Arsenic Plating 110° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	D	A	A	B		
Brass Plating																															
Regular Brass Bath 100° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	D	A	A	A	B		
High Speed Brass Bath 110° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	D	A	A	A	B		
Bronze Plating																															
Copper Cadmium Bronze Bath R.T.	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	D	A	A	A	B		
Copper-Tin Bronze Bath 160° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	D	B	A	A	C		
Copper-Zinc Bronze Bath 100° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	A	A	B		
Cadmium Plating																															
Cyanide Bath 90° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	A	A	B		
Fluoborate Bath 100° F	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	A	B	C	A	A	A	B		
Chromium Plating																															
Chromic-Sulfuric Bath 130° F	C	A	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	A	C	D	D	D	D	D	D	D	D		
Fluosilicate Bath 95° F	C	C	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	B	C	D	D	D	D	D	D	D	D		
Fluoride Bath 130° F	D	C	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	B	C	D	D	D	D	D	D	D	D		

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315  
 P.O. Box 529, Mordialloc, Victoria, 3195  
 102-104 Malcolm Road, Braeside, Victoria, 3195  
 Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3006)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy			
Black Chrome Bath 115° F	C				A	A							A	A	D		D			A			A	C	D	D				D				
Barrel Chrome Bath 95° F	D				C	A							A	A	D		D			A			A	C	D	D				D				
Copper Plating (Cyanide)																																		
Copper Strike Bath 120° F					A	A	A								A	A								C	B			A						
Rochelle Salt Bath 150° F		A				A	A						D	A	A		A							D	A	A		B			C			
High Speed Bath 180° F		A				A	A						D	A	A		A							D	A	A		B			C			
Copper Plating (Acid)																																		
Copper Sulfate Bath R.T.		D				A	A						A	A	A		D						A		D	A	A		A		D			
Copper Fluoborate Bath 120° F		D				D	A						A	A	A		D						A		D	A	B		C		D			
Copper (Misc.)																																		
Copper Pyrophosphate 140° F		A				A	A						A	A	A		A							B	A	A		A			B			
Copper (Electroless) 140° F								D					A	A	A		A						D	A	D		D			B				
Gold Plating																																		
Cyanide 150° F		A				A	A	C					D	A	A		A						B	A	A		A			D				
Neutral 75° F		C				A	A						A	A	A		A						A	A	A		A			A				
Acid 75° F		C				A	A						A	A	A		A						A	A	A		A			A				
Indium Sulfamate Plating R.T.		C				A	A						A	A	A		D						A	A	A		A			A				
Iron Plating																																		
Ferrous Chloride Bath 190° F		D				A	D						D	A	A		D					C		A	A	B		D		D				
Ferrous Sulfate Bath 150° F		C				A	A						D	A	A		D						A		A	A		B		D				
Ferrous Am. Sulfate Bath 150°		C				A	A						D	A	A		D						A		A	A		B		D				
Sulfate-Chloride Bath 160° F		D				A	D						D	A	A		D						A		A	B		C		D				
Fluoborate Bath 145° F		D				D	B						D	A	A		D						A		D	A	B		C		D			
Sulfamate 140° F		D				A	B						A	A	A		D						A		A	A		A		A				
Lead Fluoborate Plating		C				D	A						A	A	A		D						D	A	B		C		A					
Nickel Plating																																		
Watts Type 115 - 160° F		C				A	A						D	A	A		A						A		A	A		A		D				
High Chloride 130 - 160° F		C				A	A						D	A	A		D						A		A	A		B		D				
Fluoborate 100 - 170° F		C				D	A	D					D	A	A		D						A		D	A	B		C		D			
Sulfamate 140° F		C				A	A						A	A	A		A						A		A	A		A		A				
Electroless 200° F													D	A	D		D						D		A	A	D		D		B			
Rhodium Plating 120° F		D				D	D						A	A	A	D	D						A		A	A		B		A				
Silver Plating 80 - 120° F		A				A	A						A	A	A		A						A		B	A	A		A		A			
Tin-Fluoborate Plating 100° F		C				D	A						A	A	A		D						A		D	A	B		C		A			
Tine-Lead Plating 100° F		C				D	A						A	A	A		D						A		D	A	B		C		A			
Zinc Plating																																		
Acid Chloride 140° F		D				A	D						A	A	A		D						A		A	A		A		A				
Acid Sulfate Bath 150° F		C				A	A						D	A	A		D						A		A	A		B		D				
Acid Fluoborate Bath R.T.			C			D							A	A	A		D						A		D	A	B		C		A			
Alkaline Cyanide Bath R.T.			A			A	A						A	A	A		A							D	A	A		A		A				
Potash		A	A	C		A	C		B				A	B		A	B	A		B	A		A	A	A	A		B		B	A			
Potassium Bicarbonate		A	B	C		A	B	B	D				A	A		A	A	C	A	C	B	A		A	A	A		A		B	A			
Potassium Bromide		A	A	B	C	A	B	C	D	D			A	A	A		A	A	C	B	A		B	A	C	A	A		A	A	B	A		
Potassium Carbonate		B	A	A	C	A	A	C	B	B			A	B	A		A	B	A	B	A		B	A	A	A		A	B		A			
Potassium Chlorate		B	A	A	A	B	A		B	B			A	A	B		A	B	D		B	A		A	A		A		A		B	A		
Potassium Chloride		C	A	A	B	B	A	A	C	C	B	B		A	A		A	A	A	B	C	B	A		A	A		A		A		A		
Potassium Chromate			B	B	A		B	A		A			A				A	C		B			A	A	D	A		A		B	C			
Potassium Cyanide Solutions		B	A	B	A	D	A	A	D	B	B		A	A	A		A	C	A	B	A		B	A	A	C	A	B		A		A		
Potassium Dichromate		B	A	A	A	A	B	C	B	C			A	A	A		A	C	D	B	A		A	A	A	A		B		A		A		
Potassium Ferrocyanide		B	A		A	C		B	A				C	A			A										D		A		A			
Potassium Hydroxide (50%)		A	B	B	B	D	C	A	D	D	C		A	D	A	B	A	A	D	A	C	B	A		D	D	B	C	A	A	C	A		
Potassium Nitrate		B	A	B	A	B	A	B	B				B	A	A	C	A	A	B	C		B	A	C	A	A	B		A		A		A	
Potassium Permanganate		B	A	B	B	B	B	B	B				B	B	A		A	A	C	D	C	B	B	A	A	A		B		A		B		
Potassium Sulfate		B	A	B	B	A	A	A	B	B	B		B	B	A		A	A	B	C		B	A	A	A	A		A		C	A		A	
Potassium Sulfide		A	A		A	B		B	B	B	B		A		A															A				
Propane (Liquified) 1 2		A	A		A	A		A	A	B			D		A	D	A	A					D		A	A		A		D	B	D	D	A

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315

P.O. Box 529, Mordialloc, Victoria, 3195

102-104 Malcolm Road, Braeside, Victoria, 3195

Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3006)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy			
Propylene Glycol	B	B	A	A				B	B	B					A		B	B	B	B		A	A	A	A		C			A				
Pyridine		C	B	B						B	A	D		D	A	D	D			C	B	A	A	A	D	D		D	B	D	A			
Pyrogalllic Acid	B	A	A	A	B		A	B		B	B		A		A	D	A					A	A	A	A					A				
Rosins	A	A	A	A	A		B	A	C		C				A	B	A				A	A	A	A						A				
Rum		A	A										A			A	A	A			A	A	A	A	A		A			A				
Rust Inhibitors		A	A				A		A							A				A	A	A	A	A		C				A				
Salad Dressing		A	A	B			B		D				A			A	A	A			A	A	A	A	A					A				
Sea Water	A	A	C	A	C	A	C				D		A		A	A	A	A		B	A	A	A	A	A	B	B	A	A	A				
Shellac (Bleached)	A	A	A	A			A	B	B	A					A	A	A	A			A			A	A					A				
Shellac (Orange)	A	A	A	A			A	C	C	A					A		A	A			A			A	A					A				
Silicone		B	A	B			A									A	A	A			A			A	A	A	B	A	A	A				
Silver Bromide		C	C	B	D											A	C						A							A				
Silver Nitrate	B	A	B	A	D	A	A	D		D	D	A	A	B	A	A	C	A		B	A		A	A	A	C	A	C	A	A				
Soap Solutions <sup>1</sup>	A	A	A	A	C	A	B	B		B	A		B	B	A	A	A	A		B	A	A	A	A	A	A	B	B		C	A			
Soda Ash (See Sodium Carbonate)																																		
Sodium Acetate	B	A	A	B	B	A		B		C	C	A	A		A	A	B	A		B	A		A	A	D	D	C		A	A				
Sodium Aluminate	B		A	C	B	B	B				C				A	A	B	A					A	A	A	A	A	A	B	A				
Sodium Bicarbonate	B	A	A	A	A		B	A	C	C	A	A	B	B	A	A	B	A	B	B	B	A	A	A	A	A	C	A	A	A	A			
Sodium Bisulfate	A	A	A	D	B	B	C	C	D	D	A	A	B	A	A	B	C	C	B	A	A	A	A	A	B	A	C	A		A	A			
Sodium Bisulfite		A		A	A	B	C		D		A	A	B	A	A	B	D	B	B	A	A	A	A	A	A	A	C	A		A	A			
Sodium Borate	B	A		A	C		A	A		C	C		C		A		A			A				A		B	A							
Sodium Carbonate	B	A	B	B	C	A	A	B	B	B	B	A	A	B	A	A	A	A	C	B	A	A	B	A	A	A	A	A	A	A	A			
Sodium Chlorate	B	A	A	B	A	B	B			C	A	A	B	A	A	A	D	A		B	A	A	A	A	A	D	A	A	A	A	A			
Sodium Chloride	B	A	C	B	C	A	A	B	C	B	C	A	A	B	A	A	A	A	B	B	A	A	A	A	A	A	C	A	A	B	A			
Sodium Chromate	A	A	A		D		B	B		B	B				A	A	D	A			A	A	A	B	B	A		A			C			
Sodium Cyanide	B	A		A	D	A		D	D	B	B	A	A		A	A	D	C		B	A	A	A	A	A	A	D	A	A	A	A			
Sodium Fluoride	B	C		C	C	A	A	C		D	D		D	D	A		A			A	C				B	D	D	D	D	A	A			
Sodium Hydrosulfite					A	A	C						C	A	A									A	A					A	A			
Sodium Hydroxide/Caustic Soda (20%)	A	A	A	D	A	A	C	D	A			A	A	B	A	A	D	C	C	B	A	A	C	D	A	A	D	B	A	A	A			
Sodium Hydroxide/Caustic Soda (50%)	A	B		D	A	A	C	D	B		D	A	B	A	A	D	C	C	C	A	B	C	D	D	D	D	C		A	A	A			
Sodium Hydroxide/Caustic Soda (80%)	A	D		D	A	B	C	D	C			A	B	A	A	D	C	C	C	A	B	C	D	B	D	D	C		B	A	A			
Sodium Hypochlorite/Bleach <sup>3</sup> (to 20%)	C	C	C	C	A	A	D	D	D				A	B	A	A	D	A		B	C	C	D	A	A	C	D	D	B	C	B			
Sodium Hypochlorite/Bleach	D	D		D	A	A	D	D	D	A	A				A	A	A			C	C		D	B	B	C	A				A	A		
Sodium Hyposulfate		A	A	D	A	D									A												C		C					
Sodium Metaphosphate <sup>2</sup>	A		A				C	C	B	B					A		B	A			D		A	A	A	A	B	A	A	A	A			
Sodium Metasilicate	A		A		B		B	C	C						A		D						A	A	A	D	A				A	A		
Sodium Nitrate	B	A	A	A	A	A	B	B	C	A	B	A	A	B	A	A	B	A		B	A		A	A	D	C	D	B	A	C	A	A		
Sodium Perborate	B		C	B			C	C	B	B					A	A	B	A			A		A	A	A	B	D	B	A	C	A	A		
Sodium Peroxide	B	A	A	C	B		B	C	C	D	C		A		A		D	D						A	A	A	C	D	B	A	C	A		
Sodium Polyphosphate (Mono, Di, Tribasic)		A	A		D	A	A	C							A	A	B						A	A	A	A	D	A	A	A	A	A		
Sodium Silicate	B	A	B	A	C	A	B	C	C		B		A	B	A	A	C	A			A		A	A	A	A	A	A	A	A	A	A		
Sodium Sulfate	B	A	A	C	B	A	B	B	B	A	B		A		A	A	B	A		B	A	A	A	A	A	A	A	A	A	C	A	A		
Sodium Sulfide	B	A	B		D	A	B	D	D	A	B		A	B	A	A	B	A		B	A	A	A	A	A	C	A	A	C	A	A	A		
Sodium Sulfite		C	C	C	A	A	C	A					A	A	A			D		A			A	A	A	A	A	A	A	A	A	A		
Sodium Tetraborate					A								A			A	B						A	A	A	A					A	A		
Sodium Thiosulphate (-Hypo-)	A	A	A		B	A		D	D	C	B		A		A	A	C	A			A	A	A	A	A	B	A	A	C	A	A	A		
Sorghum		A	A							A							A	A					A	A	A	A	A				A	A	A	
Soy Sauce		A	A		A			A		D						A	A	A					A	A	A	A	A	A	A	D	A	A	A	
Stannic Chloride	D	D	D		D	A	B	D		D	D	A	A		A	A	C	A		B	A		A	A	A	D	A	A	A	A	A	A	A	
Stannic Fluoborate					A					D						A	C							A	A	A	A				A	A	A	
Stannous Chloride	D	D	C		D	A	A	D		D	D		A	A	A			D		A					B	C	D	D		A	A	A	A	
Starch	B	A	A		A			B		C	C		A		A	A	A	A		B			A	A	A	A	A			A	A	A	A	
Stearic Acid <sup>2</sup>	B	A	A	A	B	A	A	C	C	C	C	A	A	B	A	A	A	A		B	D		A	A	A	A	B	D	B	B	C	A	A	
Stoddard Solvent	A	A	A	A	A	A	A	A	A	B	B	A	A	A	D	A	A	A	B	D	D	A		A	A	A	B	D	D	D	D	A	A	
Styrene	A	A	A		A			A		A					A	A	A						A	A	B	D	D	D	D	D	D	A	A	A
Sugar (Liquids)	A	A	A	A	A			A	A	B	B				A	A	A	A	B		A		A	A	A	A	B			A	A	A	A	

1. P.V.C. -Satisfactory to 22° C.  
 2. Polypropylene -Satisfactory to 22° C.  
 3. Polypropylene -Satisfactory to 49° C.  
 4. Buna-N -Satisfactory for - O-Rings



# MATTHEW DAVIS Australia Pty. Ltd.

ACN 082 193 315 ABN 97 082 193 315  
 P.O. Box 529, Mordialloc, Victoria, 3195  
 102-104 Malcolm Road, Braeside, Victoria, 3195  
 Telephone: (03) 9580 0066 Facsimile: (03) 9587 2829

## Chemical Resistance Chart

A - No effect -Excellent  
 B - Minor effect -Good  
 C - Moderate effect -Fair  
 D - Severe effect -Not recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	Kynar	PVC (Type 1)	Tygon (E-3806)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Viton	Buna N (Nitrile)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy				
Sulfate Liquors	C	C		B		A	C									D				A	A	A						C		A					
Sulfur Chloride		D	D	D	D			C	D				A	C	A	A	D	A		A	D		A	C	A	D		D	D	D	C				
Sulfur Dioxide2	A	A	C	A	A	B	B				B	D	B	A	D	B	D	D	C	D	A	A	A	D	D	C	B	A	D	A	A				
Sulfur Dioxide (dry)	A	A	A	A	A	A	A	C	A	B			D	A						A	D		A	A	D	D	C	B	A	D	D				
Sulfur Trioxide (dry)	A	A	C	A				B	B	B			A	B	A	D	D	D					B	A	A	D		D	B	C	A				
Sulfuric Acid (to 10%)		D	C	C	C	A	A	D	D	D			A	A	B	A	A	D	D	B	B	A	A	A	A	C		D	D	C	A				
Sulfuric Acid (10% - 75%)2		D	D	D	D	C	B	D	D	D			A	A	B	A	B	D	D	B	C	A	B	A	A	A	D		D	D	D	B			
Sulfuric Acid (75% - 100%)			D		D	B		D				A	B	A	A	A	D				B	C		A	A	D		D			D				
Sulfurous Acid	C	C	B	C	C	A	B	D		D	D		A	B	A	A	D	D		B	A		B	A	A	C	D	B	B	C	A				
Sulfuryl Chloride													A	A										A								A			
Syrup		A	A	A	A			D					A			A	A	A	B		A		A	A	A	A		B		A	A				
Tallow		A	A		A											A	A	A		C			A	A	A	A						A			
Tannic Acid	B	A	A	A	C	A	B	B		C	C	A	A	B	A	A	B	D		B	A		A	A	A	A	D	C	A	A	A	A			
Tanning Liquors		A	A	C	A	A	A						A	B	A		B				A		A	A	A	C						A			
Tartaric Acid	B	A	B	B	C	A	B	A	C	D	D	A	A	B	A	A	B	A		B	A		A	A	A	D	C	A			A	A			
Tetrachlorethane			A			A	A						D		A	D	A	A			A		A	A	A	D			D	D	A	A			
Tetrahydrofuran		A	A		D			D	D	A	D	D		A	D	A	A			D	C	A	A	A	D	D		D	B	D	A	A			
Toluene, Toluol3	A	A	A	A	A	A	A	A	A	A	A	D	D	A	D	A	A	D	D	D	D	A	A	A	C	D	D	D	D	D	A	A			
Tomato Juice	A	A	A	A			C	C	C					A	A	B	A	B			A	A	A	A	A	A	A		A			A			
Trichlorethane		C	A		C	A	A	C		C					A	D	A							A	A	A	D	D	D	D	D	A			
Trichlorethylene2	B	A	A		B	A	A	B	A	C	B	A	D		A	D	A	C	D	D	D	C	A	A	A	D	D	D	D	D	A	A			
Trichloropropane			A				A									D	A		D					A	A	A	A					A			
Tricresylphosphate			A			B	A	A				D		A	C	C								A	A	B	D	D	A			A			
Triethylamine							A						A			B	D							A	A	A	D	B				A			
Turpentine3	B	A	A		C		A	B	C	B	B	A	A	B	A	D	A	A		D	B	A	A	A	A	D		D	D	D	A	A			
Urine		A	A		B			C		B				A			A	A	A	B	A		A	A	A	A		D	A			A			
Vegetable Juice		A	A		A			C		D						A	A	A						A	A	A	A	B	D			D	A		
Vinegar	A	A	A	A	D	A	A	B	C	D	A	A			A		B	A	B	B	A	A	A	A	A	C	B	A	C	A		A			
Varnish (Use Viton for Aromatic)	A	A	A	A	A		A	B	C					A	D	A	A				A		A	A	A	A	B	C	D			D	A		
Water, Acid, Mine		A	A		C			C	D	C			A	B		A	D	A	B		A	B	A	A	A	A		B				B	A		
Water, Distilled, Lab Grade 7		A	A		B			A		D			A	B	A	A	A	A	A		A	A	A	A	A	A		B	A	A			A		
Water, Fresh	A	A	A		A			A	C	B	D		A	B	A	A	A	A	A	A	A	A	A	A	A	A		B	A	A			A		
Water, Salt		A	A		B			B	C	D			A	B		A	A				A	A	A	A	A	A		B	A	A			A		
Weed Killers		A	A		C			C										A	A					A	A	A	B	C					A		
Whey		A	A		B												A							A	A	A	A						A		
Whiskey and Wines	A	A	A	A	D			B	B	D	D		A		A	A	A	A		B	A		A	A	A	A	B	A	A			A	A		
White Liquor (Pulp Mill)		A	A				A	D		C			A		A	A	D	A			A		A	A	A	A		A					A		
White Water (Paper Mill)		A	A				A										B	A					A	A	A	A		A					A		
Xylene2	A	A	A		A		A	A	A	A	B	A	D		A	D	A	A	D	D	D	A	A	A	A	A	D	D	D	D			A		
Zinc Chloride	D	D	B	B	D	A	B	D	D	D	D	A	A		A	A	C	A		B	A	A	A	A	A	A		A	A			A	A		
Zinc Hydrosulphite			A		D			D		D							A	C					A	A	A	A		A	A				A	A	
Zinc Sulfate	B	A	A	A	D	A	B	B	C	C	D	A	C	B	A	A	C	A		B	A	A	A	A	A	A		A	A				A	C	A

These are chemical resistance recommendations based on information from material suppliers and careful examination of available published information and are believed to be accurate. However, since the resistance of metals, plastics and elastomers can be affected by concentration, temperature, presence of other chemicals and other factors, this information should be considered as a general guide rather than an unqualified guarantee. Ultimately, the customer must determine the suitability of the material used for various solutions.

All recommendations assume ambient temperatures unless otherwise noted.

**The ratings for these materials are based upon the chemical resistance only. Added consideration must be given to selections when the chemical is abrasive, viscous in nature, or has a Specific Gravity greater than 1.1.**

1. P.V.C. -Satisfactory to 22° C.
2. Polypropylene -Satisfactory to 22° C.
3. Polypropylene -Satisfactory to 49° C.
4. Buna-N -Satisfactory for - O-Rings